



## PERFECTO STUCCOMARMO



### 1. SPECIFICATIONS AND FIELDS OF EMPLOYMENT

PERFECTO STUCCOMARMO derives from the success of STUCCOMARMO on the market, the great demand from customers to obtain this extraordinary effect also in exterior walls able to withstand the harshest weather conditions, the weather, the aggression of different environments (marine, chemical). With STUCCOMARMO we reset the technical limits (as it is a lime base product it requires a lime base without cement) PERFECTO STUCCOMARMO can be applied on a wide range of the supports (concrete, lime, old plastic plasters, and so on)

### ADVANTAGES

High breathability penetration rate of water vapour very close to that of the lime) Very high water repellence (guarantee of water resistance)

- Self-cleaning (its microstructure surface, highly water-resistant, minimizes the contact area for water and dirt and helping self-cleaning)
- High elasticity (contains micro-movements of the substrate leaving its characteristics)
- Effect anticrack -(due to the excellent flexibility of the elastomer)
- Antialga-antifungal (essential in a jackets covering to prevent the black algal)
- Excellent color resistance to ultraviolet and weather

### 2. COMPOSITION

PERFECTO STUCCOMARMO is a paste product based elastomeric emulsion modified with siloxane resin, selected aggregates, pigments resistant to light and weathering, specific additives.

### 3. METHOD OF APPLICATION

Mortar and lime or cement, paint or mineral and synthetic coatings, perfectly dry and cohesive are suitable, Apply a coat of SILOSSANA PRIMER diluted 100% with water; Spread a layer of STUCCOMARMO with stainless steel trowel, and in order to level the support, after drying, if necessary, and to increase the final lucidity repeat with another layer. Apply in small batches using the put on take of technique, as soon as the product starts to dry press heavily with a stainless steel trowel until you get the desired finish. Do not apply

on surfaces where there is shown signs of rising damp or infiltration.

### 4. TECHNICAL DATA

**SPECIFIC WEIGHT:** 1,629 Kg./Lt. ± 5%

**VISCOSITY' BROOKFIELD:** cPS 52200 ±20% - R7 - RPM 20 - 25°C

**PH:** 8,95 ±1

**DRYING:** dry to the touch: 4 hours at 20°C, with humidity less than 60% completely dry: 48 hours with humidity less than 60% .

**TEMPERATURE OF APPLICATION:** between 5°C e 30°C.

**COVERAGE RATE:** 1,4 – 1,8 m<sup>2</sup>/Lt.

**COLOURS:** to be chosen from our colour chart

**PERMEABILITY TO WATER VAPOR:** sd = 0.15 m (UNI 8202/43).

**WATER ABSORPTION: W24 =** 0.02 kg / m h0,5 (DIN 52013).

**PACKAGE:** Lt. 14, Lt. 4,67, polypropylene can

**PRESERVATION:** 24 months in the intact packages, away from temperature changes

**HS-CODE:** 32091000

### 5. ITEM OF SPECIFICATIONS

Decoration and protection of exterior surfaces with plaster elastic siloxane with the spatulata plaster effect, such as PERFECTO STUCCOMARMO produced by Spiver Srl, elastomeric emulsion base modified with siloxane resin, selected aggregates, pigments resistant to light and weathering, specific additives; consolidating after treatment with a coat of PRIMER SILOSSANA of Spiver Srl diluted with 50% water of the tint chosen by P.M.

Price inclusive of the material and implementation, except the scaffoldings per square metre: €.....

NB The above-mentioned data are susceptible of variations. Spiver Ltd. is not responsible for any negative result depending on the application of the product out of the Company's control and on the agents unrelated to the product quality.



*Emotion with paint ...*

**SPIVER s.r.l.**

contradaBabbaurra S.S. 122

93100 Caltanissetta ( CL )

Tel. +39 0934 57 77 91 Fax +39 0934 58 87 95

[www.spiver.it](http://www.spiver.it) - [info@spiver.it](mailto:info@spiver.it)

**Scheda Tecnica: PERFECTO STUCCOMARMO SP 027. Rev.1** La presente scheda annulla e sostituisce le precedenti